



Series for Cotton

DIKAPHOR		Series 	GP	AJ	SA	DSL	JG
Properties	Color Index no (Cl. No)		24	86/113	90/134	220	353/357
	Appearance (suspension)		L/yellow	L/yellow	Ivory	L/yellow	Ivory
	Color Shade		N.W-B	N.W-B	N.W-R	N.W-R	N.W-R
	Light Fastness		2	2	2	2	2
Stability	Chlorite Bleach		?	?	?	?	?
	Peroxide Bleach		✘	✘	✘	✘	?
	Acid(pH~range)		5 ~12	7 ~12	7 ~12	3.5 ~ 12	2 ~12
	Hard water		✘	✘	✘	✘	?
Dosage	Exhaustion(%)		~ 0.3	~ 0.2	~0.2	~ 0.4	?
	Paddling(pick Up <80%), g/L		4~6	3~4	2~3	4~6	~10
Dyeing	Exhaustion Method		✘	✘	✘	✘	?
	Best dyeing Temp(Exhaustion)		80°C	60- 80°C	60- 80°C	80°C	***
	Dyeing temp(Exhaustion)		~ 100°C	~ 100°C	~ 100°C	~ 100°C	***
	Continuous Method(Pad-baker)		✘	?	?	✘	✘
Example	✘ Excellent or Stable		N.W. : Natural White				
	? Moderate or Limited		R,2R,3R, : Reddish				
	? Not recommended		B2B,3B : Bluish				
Remark	*** Not recommended						

DIKAPHOR  OPTICAL BRIGHTENERS